









## RECOLOUR

### CORK FLOATING FLOOR – WEARPLUS® FINISH














#### TECHNICAL SPECIFICATION

GENERAL DEFINITION AND PRODUCT COMPOSITION	
Definition	Loose laying Cork Floor Panels, with 10,5mm thickness, to be used as an interior floor covering, in accordance with EN ISO 20326.
Dimensions	1164 x 300 x 10.5 mm
Finish	WEARPLUS® High performance PUR HotCoating® finished with waterborne lacquer, with very low VOC content and extremely high wear, impact and chemical resistance. With CleanSurface powered by Microban® antimicrobial technology.
Product structure	 <p>Top layer: 3 mm thickness high-density agglomerated cork floor covering according to EN 12104. Core layer: HDFCORE+ High-density fibreboard 6 mm, with very low formaldehyde content (E1), CARB ATCM Phase II and TSCA Title VI compliant, and very high moisture resistance properties. Backing layer: 1.5 mm acoustical CleanCork underlay with integrated Microban® antimicrobial protection. Edges: 4 sides bevelled.</p>
Installation	Glue-less Uniclic® locking system, installed floating according to installation instructions.
TECHNICAL DATA	
Classification	  <p>EN ISO 10874</p> <p>Domestic 23   Residential areas with high traffic Commercial 32   Public areas with medium traffic</p>
Length and width	 <p>EN ISO 24342</p> <p>1164 x 300 mm ± 0.10%</p>
Overall thickness	 <p>EN ISO 24346</p> <p>10.5 mm ± 0.20 mm</p>
Thickness of cork surface layer	 <p>EN ISO 24340</p> <p>3 mm -0/+0.20 mm</p>



DELIVERING NATURE

**RECOLOUR**  
CORK FLOATING FLOOR – WEARPLUS® FINISH  
TECHNICAL SPECIFICATION

<b>TECHNICAL DATA</b>			
Density of cork surface layer		ISO 3850	> 500 Kg/m <sup>3</sup>
Squareness Straightness		EN ISO 24342	< 0.3 mm < 0.2 mm
Flatness of the panel Length - Concave / Convex Width - Concave / Convex		EN ISO 20326	< 0.10 % / < 0.5 % < 0.05 % / < 0.1 %
Openings between panels Average / Individual values		EN ISO 20326	< 0.10 mm / < 0.15 mm
Height difference between panels Average / Individual values		EN ISO 20326	< 0.15 mm / < 0.20 mm
Dimensional variation caused by changes in atmospheric humidity		EN ISO 20326	< 0.25 %
Residual indentation		EN ISO 24343-1	< 0.25 mm
Locking strength Long / Short		EN ISO 24334	> 3 kN/m / > 4 kN/m
Thickness Swelling		ISO 24336	< 12%
Castor chair		ISO 4918	No disturbance to the surface other than slight change in appearance and no delaminating shall occur
Simulated movement of a furniture leg		EN ISO 16581	No damage shall be visible when tested with foot type 2
Mass per unit area		EN ISO 23997	7900 g/m <sup>2</sup>
Abrasion resistance		EN 14354	> 7000 rev
Impact resistance (small ball)		EN 438-2	> 40 N
Scratch resistance		EN 438-2	Rating 2 (2.0 N)
Impact noise reduction		EN ISO 10140-3	ΔL <sub>w</sub> = 19 dB
Thermal resistance		EN 12667	0.10 m <sup>2</sup> .K/W
Light fastness		EN ISO 105-B02	5 (blue scale)






DELIVERING NATURE

# RECOLOUR

## CORK FLOATING FLOOR – WEARPLUS® FINISH

### TECHNICAL SPECIFICATION

#### TECHNICAL DATA

Slip resistance		EN 13893	Technical class DS dynamic coefficient of friction $\mu > 0.30$
Reaction to fire		EN 13501-1	Class C <sub>fl</sub> -s1
Formaldehyde emission		ENV 717-2	Formaldehyde Class E1
VOC emission		ISO 16000 parts 3, 6, 9	Fulfilled AgBB scheme Fulfilled French Classification A+

#### GENERAL DATA

Packaging	Floating floor panels are dispatched in cardboard trays wrapped in shrinking foil, providing suitable protection for normal transport and storage conditions. Packages are identified by a label and/or inkjet printing and palletized. Each pallet is over strapped and wrapped with stretch film. 6 planks/pack; 2.1 m <sup>2</sup> per pack; 48 packs per pallet; 100.8 m <sup>2</sup> per pallet. Weight per pack: 17 Kg.		
Underfloor heating	Suitable for hot-water and electrical underfloor heating. The recommended maximum surface temperature is 28°C. The specific floating floors installation instructions for underfloor heating must be observed.		
Limited warranty	We certify that the product is free from manufacturing and structural defects and will remain free of these defects. We guarantee that the surface finish will not wear through within 15 years (Residential) or 5 years (Commercial), under normal residential or commercial use and with proper maintenance. <i>Note: The specific warranty terms and conditions must be observed. For warranty conditions, see <a href="http://www.granorte.com">www.granorte.com</a>.</i>		
Environment	RECOLOUR cork floating floors are made from more than 80% renewable raw materials (cork and wood) and 30% of recycled by-products (cork and wood). Contains no PVC, no plasticizers other substances hazardous to health or environment.		



FSC® certified products are available upon request

GRANORTE reserves the right to make changes to material and structure to improve the quality or technical performance.